

Multi Universal

Polyester body putty

V01
02/2018

:: CHARACTERISTIC

Multi Universal is a filling and base putty quality with very high thixotropic properties.

- high viscosity
- concentrated filler
- for use on steel surfaces only

:: AREA OF APPLICATION

For filling in deep uneven areas and dents on vehicle bodywork in the area of cars, lorries, buses and railway vehicles

:: PRODUCT DATA

MATERIAL DATA

Delivery viscosity at 20°C:	Paste-like
VOC - content:	2004/42/IIIB (b) (250) < 250g/l
Colour:	Dark-beige

HANDLING

Base

The surface must be clean, dry and grease-free.

Dosing

Addition of 2 % by weight hardener paste.

An overdosing of the hardener paste must be avoided. Bleeding through and colour changes in the topcoat system may occur.

Pot Life

At 18°C – 20°C ambient temperature, 4 - 5 minutes.

Application

Spread on with spatula.

It is not recommended to use the putty below +10°C ambient temperature.

Drying Time

Air drying at a room temperature of 20° C, 20 – 30 minutes.

Warmth reduces, cold increases the drying or hardening time.

Sanding

Following the specified drying time.

As filling putty

Hand sanding, dry: P80 - P120

Machine sanding, dry: P120 - P240

Reworking

Multi Universal can be reworked with the following
CS products: - Elastic weiss or Elastic beige and Spray

Storage

12 months at 20°C in closed original container.

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore,

TECHNICAL DATASHEET



our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE